

# MICROTUFF®-F (Barretts, MT) high purity Montana talc



MICROTUFF®-F is a fine particle size platy talc with an FDA surface coating approved under the following: 21CFR 175.500, 21CFR 182.90, 21CFR 177.1520, 21CFR 174.5 (d) and 21CFR 178.3400. MICROTUFF®-F provides high modulus while maintaining the inherently high impact strength of the polyolefin. When used in combination with the new generation high performance polyolefins, MICROTUFF®-F opens new opportunities in food applications, such as thermoformed containers, blown film and injection molded containers and parts.

BMI's Montana Microtuff product contains no detectable quantities of any of the asbestiform minerals.

## Physical Properties

(typical)

Median Particle Size (microns)	1.2
Specific Gravity	2.8
Dry Brightness (Hunter Y, Rd value)	89.5
Bulk Density (pounds/ft <sup>3</sup> )	9.5
(grams/cc)	0.15
Tap Density (pounds/ft <sup>3</sup> )	23
(grams/cc)	0.37
pH Value	8.8
Hegman Fineness	6



## Chemical Composition

(typical)

Silicon Dioxide	SiO <sub>2</sub>	59%
Magnesium Oxide	MgO	31%
Calcium Oxide	CaO	0.3%
Aluminum Oxide	Al <sub>2</sub> O <sub>3</sub>	2.0%
Iron As	Fe <sub>2</sub> O <sub>3</sub>	1.1%
Loss on Ignition	L.O.I.	6.5%
Moisture (% weight loss @ 110° C)	H <sub>2</sub> O	>0.5%

All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use. All information given and recommendations made herein are based upon our research and are believed to be accurate, but no guarantee, either expressed or implied, is made with respect thereto or with respect to the infringement of any patent. SMI MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. Inconsistent terms and conditions contained in Buyer's purchase order shall not be binding on SMI/BMI unless reflected in writing signed by SMI/BMI's representative. The information contained herein is not to be copied or otherwise used in any publication in whole or in part, without written permission from Specialty Minerals Inc./Barretts Minerals Inc.

## Sales Offices

Bethlehem, PA • 1-610-997-8394  
 Barretts, MT • 800-336-9008  
 www.mineralstech.com

MICROTUFF® is a trademark of Minerals Technologies Inc. or its subsidiaries  
 ©Specialty Minerals Inc. 6/2007

