

# ViCALity ALBAFIL®

USP / FCC Precipitated Calcium Carbonate

## ViCALity® PCC Products

ViCALity ALBAFIL® Precipitated Calcium Carbonate (PCC) is one of a family of eight low lead calcium carbonates available in a wide variety of sizes and shapes to meet the needs of formulators of foods, drugs, nutritionals and personal care products. Containing less than 500 ppb lead, the ViCALity® PCC's are suitable for many applications that must meet the lead requirements of California Proposition 65.

ViCALity® PCCs meet and exceed the requirements for Calcium Carbonate of the United States Pharmacopeia 24 and of the Food Chemicals Codex, Fourth Edition. All are certified as Kosher. Calcium carbonate is Affirmed GRAS (Generally Recognized As Safe) by the US FDS (21 CFR 184.1191), with no limitations other than good manufacturing practices. This allows the use of calcium carbonate as both a direct and indirect food additive. ViCALity® PCC products are manufactured in the Specialty Minerals plant in Adams, MA under stringent quality assurance procedures and good manufacturing practices.

## ViCALity ALBAFIL® PCC

ViCALity ALBAFIL® PCC is a low lead prismatic calcite particle which is 0.7 micron in size. It is the smallest particle sized product in the ViCALity® PCC family, which results in low powder density.

CalEssence® 70 PCC is the ultra-low lead equivalent of ViCALity ALBAFIL® PCC.

### Characteristics:

- Smallest particle size
- High surface area
- Moderately high oil absorption
- Low density
- Very Mild abrasive
- Good suspendability
- Less than 500 ppb lead
  - Good for most Proposition 65 uses
- High elemental calcium level
  - ~40% calcium
- High bioavailability – equal to milk calcium
- Economical in use
- No calories, carbohydrates or fats
- Non-dairy, lactose-free

## Scanning Electron Micrograph:



magnification: 10,000x

## Applications:

ViCALity ALBAFIL® PCC is an excellent choice where the smoothest texture is desired. In most solid foods, the larger Heavy and Extra Heavy grades are small enough to remain undetected in taste, and taste tends to improve as the particle size increases. However, in some product types, especially liquids, ice creams and some soft, chewy forms, the presence of such large particles may be apparent. In those instances, a smaller grade like ViCALity ALBAFIL® PCC is usually better. The high surface area of this grade also makes it an excellent detackifier for natural rubber. Its mild abrasivity suits it for toothpastes for artificial teeth.

Some uses for ViCALity ALBAFIL® PCC are:

- Frozen dairy products
- Liquid meals, diet drinks & infant formulas
- Soy or milk beverages
- Soft chew calcium supplements
- Liquid or soft chew antacids at lower dosages
- Antacid and calcium supplement tablets, but only when a large tablet is desired
- Solid confectionery dosage forms
- Specialty toothpastes for bridgework
- Natural rubber detackification
  - Gloves, condoms, slab, crumb, dip

The use of ViCALity ALBAGLOS® PCC may be preferred in high solids liquid systems with flow problems. ViCALity ALBAGLOS® PCC contains 15% of a larger PCC particle, which improves flow properties over those of ViCALity ALBAFIL® PCC.




## Typical Physical Properties

Crystal habit	Calcite
Particle Shape	Prismatic
Particle Size, median, microns	0.7
Mode, microns	0.7
Surface Area, meters <sup>2</sup> /gram	7.0
Oil Absorption, grams oil/100 grams	32
Tapped Density, grams/cc	0.60
pounds/ft <sup>3</sup>	37.5
Bulk Density, grams/cc	0.29
pounds/ft <sup>3</sup>	18.1
Specific Gravity	2.71
pH	9.8
Moisture, %	0.2
Dry Brightness, Hunter Y, Rd value	98
Lead, parts per billion	< 500
Solubility in water, pH 7	Insoluble
in acid	Soluble


*Note:*

*These are typical values, and should not be used to set specifications.*

**Cumulative Particle Size Distribution**  
Total % by weight below each micron size



**Particle Size Distribution**  
% by weight at each micron size



## Dispersion and Slurry Viscosity:

ViCALity ALBAFIL<sup>®</sup> PCC is one of the more difficult grades to disperse. Use high shear, with high solids, to achieve the small particle size.

After high shear dispersion for 10 minutes, the Brookfield RVT viscosity of a slurry in water, measured at 20 rpm, is:

30% solids . . . . .	1,700 cps
40% solids . . . . .	5,700 cps
50% solids . . . . .	14,000 cps

If problems are encountered in preparing high solids slurries, an appropriate pigment dispersant should be used.

**Product Code:** 100-0440-3

## Specialty Minerals Inc.

35 Highland Avenue  
Bethlehem, PA 18017

## For order placement:

Customer Service – toll free: 877-684-7627  
Fax: 413-743-4527

## Packaging:

ViCALity ALBAFIL<sup>®</sup> PCC is packaged in 50 pound, three-ply kraft bags. The standard shipping unit is a 54" x42" 2-way pallet of 50 bags, a total of 2,500 pounds. Pallets include slipsheets and shrink wrap. Semi-bulk packaging, typically in 2,000 pound sacks, is also available. Contact Customer Service or your SMI Representative for details.

## FDA Codes:

The Specialty Minerals plant in Adams, MA is registered with the US FDA as a Drug Establishment. The registration number for the plant is 1214544. The National Drug Code (NDC) for ViCALity ALBAFIL<sup>®</sup> PCC is 053044-0440-3 for product supplied in 50 pound bags.

## Visit Our Website:

[www.mineralstech.com](http://www.mineralstech.com)

## For Information and Samples:

Sales: 1-610-997-8394  
Email: [smi.adamscustserv@mineralstech.com](mailto:smi.adamscustserv@mineralstech.com)

All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use. All information given and recommendations made herein are based upon our research and are believed to be accurate, but no guarantee, either expressed or implied, is made with respect thereto or with respect to the infringement of any patent. SMI MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. Inconsistent terms and conditions contained in Buyer's purchase order shall not be binding on SMI/BMI unless reflected in writing signed by SMI/BMI's representative. This information is not to be copied, used in evidence, released for publication or public distribution without written permission from Specialty Minerals Inc./Barretts Minerals Inc.