

MICROTUFF® AG talc

appearance grade talcs

MICROTUFF® talc products are produced in Barretts, Montana from an extensive deposit of high quality talc ore. These products are characterized by a platy shape, closely controlled particle size distribution, and no detectable quantities of any of the asbestiform minerals. This family includes a series of five products ranging from 6 microns top size to 44 microns top size.



They are specifically designed for polymer applications where color of the finished part is of critical importance. In addition to superior color, polyolefin compounds filled with MICROTUFF® AG talc products have enhanced long term heat stability when compared to compounds filled with unmodified talcs.

Typical Properties

MICROTUFF® AG	609	101	121	262	445
Median Particle Size (microns)	0.8	1.0	1.3	2.3	5.5
Specific Gravity	2.8	2.8	2.8	2.8	2.8
Dry Brightness (Hunter Y.Rd value)	90	90	90	90	87
Bulk Density (pounds/ft³)	6.4	6.4	9.5	12.5	21
(grams/cc)	0.10	0.10	0.15	0.20	0.34
Tap Density (pounds/ft³)	20	22	22.6	34	49
(grams/cc)	0.32	0.35	0.36	0.54	0.78
Retention 325 Mesh, %	nil	nil	nil	trace	0.6
pH Value	8.8	8.8	8.8	8.8	8.8

Chemical Composition (typical)

Silicon Dioxide	SiO ₂	60%
Magnesium Oxide	MgO	33%
Aluminum Oxide	Al ₂ O ₃	1.0%
Iron As	Fe ₂ O ₃	1.2%
Loss on Ignition	L.O.I.	5.5%
Moisture (% weight loss @ 110° C)	H ₂ O	<0.5%



All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use. All information given and recommendations made herein are based upon our research and are believed to be accurate, but no guarantee, either expressed or implied, is made with respect thereto or with respect to the infringement of any patent. SMI MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. Inconsistent terms and conditions contained in Buyer's purchase order shall not be binding on SMI/BMI unless reflected in writing signed by SMI/BMI's representative. This information is not to be copied, used in evidence, released for publication or public distribution without written permission from Specialty Minerals Inc./Barretts Minerals Inc.

Sales Offices

Bethlehem, PA 1-610-997-8394
 Barretts, MT 800-336-9008
www.mineralstech.com

MfAG0011198
 MICROTUFF® is a registered trademark of
 Minerals Technologies Inc. or its subsidiaries.
 ©Specialty Minerals Inc. 1998