



Cellflo®

Product Description

Cellflo® is a cellulose product made from select kiln-dried hardwood and ground to meet metalcasting needs. The ability of Cellflo® to absorb and hold water slows drying of sand mixtures, helping to minimize brittle and lumpy mixtures and improve collapsibility at shakeout.

Typical Analysis

Property	Value
Moisture(%)	10% maximum
Alumina, Al ₂ O ₃	520 – 640 (target 580)
Iron Oxide, FeO, Fe ₂ O ₃	5.4-9.0

Dry Particle Size - % Retained on U.S. Sieve No.

Property	Value
60 mesh	0.1% maximum
80 mesh	10.0% maximum
100 mesh	0.0% maximum
Passing 100	65.0% maximum

Microbiological

Property	Value
Standard Plate Count	50,000/gm maximum
Coliform	250/gram maximum
E. Coli	Negative
Yeast	2,500/gram maximum
Mold	2,500/gram maximum
Salmonella	Negative/25 grams

All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use. All information given and recommendations made herein are based upon our research and are believed to be accurate, but no guarantee, either expressed or implied, is made with respect thereto or with respect to the infringement of any patent. NEITHER MINERALS TECHNOLOGIES NOR ANY OF ITS AFFILIATES MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. Inconsistent terms and conditions contained in the buyer’s purchase order shall not be binding on MINERALS TECHNOLOGIES unless reflected in writing signed by MINERALS TECHNOLOGIES’ representative. The information contained herein is not to be copied or otherwise used in any publication in whole or in part, without written permission from MINERALS TECHNOLOGIES.

