

T100NR-E

2.5 MM THERMOPLASTIC WATERPROOFING MEMBRANE

DESCRIPTION

T100NR-E is a 2.5 mm thick homogenous non-reinforced PVC-P thermoplastic waterproofing membrane for tunnel projects with excellent puncture and elongation properties. Membrane is dual color with black bottom and a integral yellow signal layer on the top. T100NR-E is resistant to root penetration, micro-organisms and natural aggressive mediums in ground water and soil.

APPLICATIONS

T100NR-E primary application is to waterproof bored rock tunnels and associated stations and shafts. The membrane is part of a system that includes a PVC water-barrier sectional grid and pre-installed remedial grout tubing network. T100NR-E is suitable on wet or damp substrates and is installed with the yellow signal layer facing the installer and is secured into position in accordance with CETCO membrane installation guidelines. Field seaming is

accomplished by fusing the PVC-P membrane using conventional welding equipment in accordance with CETCO installation guidelines. Per project requirements, double channel welding equipment may be used allowing for air pressure testing of the air channel between the two welds.

CHARACTERISTICS/ ADVANTAGES

- High resistance to aging
- High tensile strength and elongation
- Resistant to root penetration
- Resistant to micro-organisms and natural aggressive mediums in ground water and soil
- High resistance to mechanical impact
- High dimensional stability
- High flexibility in cold temperatures
- Heat weldable
- Can be installed on damp and wet substrate

LIMITATIONS

The membrane is not prolonged UV stabilized and must not be installed on structures permanently exposed to UV light and weathering. Consult CETCO for additional technical data and installation guidelines. Refer to Material Safety Data Sheet for health and safety information.

APPEARANCE

2.5 mm roll sheet membrane with smooth surface; yellow top layer; black bottom layer.

ROLL SIZE

2.2 M x 20 M.

STORAGE

Store in dry conditions. Protect from direct sunlight, rain, snow and ice. Product does not expire if correctly stored.

TECHNICAL DATA		
MATERIAL PROPERTIES	TEST METHOD	NOMINAL VALUE
Water Tightness To Liquid Water	EN 1928B	PASS
Resistance to Static Load	EN 12730	≥ 20 kg
Tensile Strength	EN 12311-2	≥ 17 N/mm ²
Elongation at Break	EN 12311-2	≥ 300%
Durability of Water Tightness Against Ageing	EN 1296 and EN 1928	PASS
Resistance to Impact	EN 12691	≥ 900 mm
Resistance to Tear (Nail Shank)	EN 12310-1	≥ 300 N
Reaction to Fire	EN 13501-1	CLASS E
Joint Strength	EN 12317-2	≥ 700 N/50 mm
Water Vapor Diffusion Resistance	EN 1931	18,000 μ (± 5,400)
Peel Resistance of Joint	EN 12316-2	≥ 150 N/50 mm
Dimensional Stability	EN 1107-2	≤ 2%
Foldability at Low Temperature	EN 495-5	≥ -25° C
Visible Defects	EN 1850-2	PASS
Durability of Water Tightness Against Chemical (28 days/23°C)	EN 1847	PASS
Application Temperature Range	—	+4°C min. / +40°C

North America: 847.851.1800 | 800.527.9948 | www.cetco.com

UPDATED: JUNE 2015

© 2015 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.CETCO.com. CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

