

the subsurface materials. Ensure that the casing is clean and watertight prior to placement in the drilled shaft excavation. Use casing with an outside diameter not less than the specified drilled shaft diameter.

00512.14 Drilling Slurry - Furnish drilling slurry meeting one of the following requirements:

(a) Mineral Slurry - Use mineral slurry conforming to the following requirements:

Property	Test	Requirement
Density	Mud Density API * 13B-1, Section 1	64 - 75 lb./cu. ft.
Viscosity	Marsh Funnel and Cup API * 13B-1, Section 2.2	26 - 50 sec./qt.
pH	Glass Electrode, pH Meter, or pH Paper	8 - 11
Sand Content	Sand API * 13B-1, Section 5	4.0 % max.

Maintain slurry temperature at 40 °F or more during testing.

* American Petroleum Institute

(b) Synthetic Slurries - Select synthetic slurries from the QPL. Use synthetic slurries according to the manufacturer's recommendations and the Contractor's quality control plan. The sand content of synthetic slurry shall be less than 2.0 percent (API 13B-1, Section 5) prior to final cleaning and immediately prior to concrete placement.

(c) Water Slurry - Water may be used as slurry when casing is used for the entire length of the drilled shaft. Use of water slurry without full-length casing will only be allowed with the Engineer's approval. Use water slurry conforming to the following requirements:

Property	Test	Requirement (Maximum)
Density	Mud Weight (Density) API 13B-1, Section 1	70 lb./cu. ft.
Sand Content	Sand API 13B-1, Section 5	2.0 %

Do not use blended slurries.

00512.15 Crosshole Sonic Log (CSL) Access Tubes - Furnish steel crosshole sonic log (CSL) access tubes meeting the following requirements:

- Steel access tubes shall be at least 1 1/2 inch inside diameter Schedule 40 pipe conforming to ASTM A 53, Grade A or B, Type E, F, or S.
- Use access tubes having a round, regular inside diameter free of defects and obstructions, including all pipe joints, in order to permit the free, unobstructed passage of the source and receiver probes used for the testing. Ensure that access tubes are watertight, free from corrosion with clean internal and external faces to ensure good bonding between the drilled shaft concrete and the access tubes. Fit the access tubes with watertight caps on the top and bottom.
- Access tube acceptance will be based on manufacturer's certification that the furnished material meets the requirements of this Specification.