

# ACCU-VIS<sup>®</sup>/CETCO<sup>®</sup> CRUMBLES

## LIQUID DRILLING FLUID POLYMER

### DESCRIPTION

ACCU-VIS/CETCO CRUMBLES blends a granular bentonite with a quick activating liquid polymer to form a slurry that provides an economical way to seal and grout boreholes, well casings, and earthen structures. Once set, the slurry forms a complete grout seal with low permeability.

### RECOMMENDED USE

To decommission abandoned boreholes and grout geothermal heat loops.

### CHARACTERISTICS

- Delayed hydration, allowing bentonite to expand in borehole
- Flexible seal with a low permeability; protects aquifer from surface contaminants
- Generates no heat of hydration
- Minimal grout settlement
- Pumps with gear pump at reduced pressure

### MIXING AND APPLICATION

Add 8 ounces ACCU-VIS to 24 gallons (0.25 liters per 109 liters) of freshwater and mix well. Quickly add one 50 lb bag (22.7 kg) of CETCO CRUMBLES to the ACCU-VIS slurry while mixing gently. Start pumping when the CETCO CRUMBLES are completely dispensed into water/polymer mixture. After the batch is pumped, flush pump, hoses, and tremie pipe with freshwater.

### SEALING CASING

Pump ACCU-VIS/CETCO CRUMBLES slurry through a tremie pipe inserted down the annular space. Fill the annulus from the bottom up and withdraw the tremie pipe slowly as the slurry is discharged. Pump until the grout returned at the surface is the same density as the grout being pumped into the hole.

### DECOMMISSIONING AND ABANDONING BOREHOLES

Pump the pre-mixed ACCU-VIS/CETCO CRUMBLES slurry through an open-ended drill pipe or tremie pipe. Fill the hole from the bottom up, and withdraw the drill or tremie pipe slowly as the hole fills.

### PACKAGING

CETCO CRUMBLES, ~50 lb (22.7 kg) bags, 48 per pallet.  
ACCU-VIS, ~44 lb (19.96 kg) pail, 32 per pallet. All pallets are plastic-wrapped.



### TYPICAL PROPERTIES

Density	9.3 lbs/gallon – 0.92 kg/l
Permeability	1.0 x 10 <sup>-8</sup> cm/sec (in freshwater)
Thermal Conductivity	0.45 Btu/hr/ft/F; 0.75 watts/metre °C
Total Active Solids	20.0% by weight
Yield	3.5 ft <sup>3</sup> - 0.1 m <sup>3</sup>

### GROUT VOLUME REQUIREMENTS

Diameter (inches)	Gallons/Foot	Feet/Gallon
2	0.16	6.25
4	0.65	1.54
6	1.47	0.68
8	2.61	0.38
10	4.08	0.25
12	5.87	0.17
14	8.00	0.13
16	10.50	0.10
18	13.20	0.08

NOTE: Volume of Annular Space = Volume of Hole – Volume of Casing O.D.

North America: 847.851.1800 | 800.527.9948 | [www.CETCO.com](http://www.CETCO.com)

UPDATED: MAY 2022

© 2022 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit [www.CETCO.com](http://www.CETCO.com). CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

FORM: TDS\_ACCU-VIS\_CETCO\_CRUMBLES\_AM\_EN\_202205

