

PREMIUM GEL®

API BENTONITE



Certified to
NSF/ANSI/CAN 60

DESCRIPTION

PREMIUM GEL is a 200 mesh, 90 bbl yield sodium bentonite for freshwater drilling, slurry walls, and tunnel boring. PREMIUM GEL complies with API 13A Section 9, Specifications for Drilling Fluid Materials. PREMIUM GEL is certified to NSF/ANSI/CAN Standard 60, Drinking Water Treatment Chemicals - Health Effects.

RECOMMENDED USE

May be used for all types of freshwater mud rotary drilling where higher solids are desired. PREMIUM GEL can also be used as a seal for earthen structures, slurry trenching, tunnel boring, and foundation drilling.

CHARACTERISTICS

- Cools and lubricates bit
- Mixes quickly and easily
- Reduces fluid loss into the formation
- Removes cuttings
- Stabilizes borehole

MIXING AND APPLICATION:

Mixing ratios are based on the use of freshwater; water purity will affect bentonite performance. For best results, acidic and hard make-up water should be pretreated with SODA ASH to a pH of 8.5-9.5. Add PREMIUM GEL slowly through jet/hopper mixer.

PACKAGING

~50 lb (~22.7 kg) bag, 48 per pallet, ~100 lb (~45.4 kg) bag, 35 per pallet, ~1 ton or ~2 ton supersacks, or bulk. All pallets are plastic-wrapped.

NOTE

PREMIUM GEL is manufactured marketed by AMERICAN COLLOID COMPANY (ACC). CETCO sells PREMIUM GEL in an AMERICAN COLLOID COMPANY (ACC) branded bag.

DRILLING FLUID AND SLURRY TRENCHING - PREMIUM GEL MIXING RATIO IN POUNDS (KG) PER 100 GALLONS (380 LITERS) OF WATER		
Condition	Lbs (kg) of PREMIUM GEL	% Solids
Normal Conditions	30 - 50 lbs (13.5 - 22.5 kg)	3.5 - 5.7%
Sand and Gravel	50 - 70 lbs (22.5 - 31.5 kg)	5.7 - 7.7%
Fluid Loss Control	70 - 80 lbs (31.5 - 36 kg)	7.7 - 8.8%
SLURRY PROPERTIES - 6.04% SOLIDS		
Property	Typical Value	Specification/Procedure
Viscosity FANN 600 rpm	40 cps	30 cps Min - ACC-TP-2005
Viscosity FANN 6 rpm	11 cps	ACC TP-2005
Viscosity FANN 3 rpm	11 cps	ACC TP-2005
Yield - 42 gal bbl of 15 cps slurry/ton	90 to 120 bbl/tn	90 Min - ACC-TP-2001
Marsh Funnel, seconds/quart	42 seconds	ACC TP-1014
Apparent Viscosity (AV)	15 to 25 cps	ACC TP-2005
Plastic Viscosity (PV)	9 to 10	ACC TP-2005
Yield Point, lb/100 ft ²	15 to 25 lb/100 ft ²	ACC TP-2005
Filtrate, 30 minutes @ 100 psi, ml	13 to 15 ml	15 ml Max - ACC-TP-2003
Filter Cake, in	3/32 in	N/A
pH	9.03	ACC TP-1018
GENERAL PROPERTIES		
Property	Typical Value	Specification/Procedure
Moisture %	7.4%	ACC TP-2006
Free Swell	28	ASTM D-5890
Plate Water Absorption	622.80%	ASTM E946-92
Specific Gravity	2.5	Generally Recognized
Bulk Density Non-compacted	53 lbs/ft ³	ACC TP-1005
Bulk Density Compacted	72 lbs/ft ³	ACC TP-1005
Grit % (<75 micron)	3.2%	4.0% Max - ACC-TP-2004
Particle Sizing	74% Min passing #200 mesh sieve	ACC TP-1015

North America: 847.851.1800 | 800.527.9948 | www.CETCO.com

UPDATED: MAY 2023

© 2023 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.CETCO.com. CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

