

REACTIVE CORE MAT™

WITH APATITE

DESCRIPTION

REACTIVE CORE MAT™ with Apatite is a permeable composite of geotextiles and a mineral that adsorbs and sequesters certain metals from water.

APPLICATION

REACTIVE CORE MAT™ with Apatite is designed for use in the following applications:

- In-situ subaqueous cap for contaminated sediments or post-dredge residual sediments
- Embankment seepage control
- Groundwater remediation

BENEFITS

- REACTIVE CORE MAT™ with Apatite provides a reactive material that treats contaminants which are carried by advective or diffusive flow
- Reactive cap allows for thinner cap thickness than a traditional sand cap
- Geotextiles provide stability and physical isolation

AVAILABILITY

REACTIVE CORE MAT™ with Apatite is available from the following CETCO plant location:

- 218 NE Industrial Park Rd., Cartersville, GA

PACKAGING

15' x 100' rolls, packaged on 4" PVC core tubes wrapped with polyethylene plastic packaging.



REACTIVE CORE MAT™ with Apatite is designed to provide a simple method of placing active materials into subaqueous sediment caps.

TESTING DATA

PHYSICAL PROPERTIES		
PROPERTY	TEST METHOD	RESULTS
APATITE¹		
Bulk Density Range	CETCO Test Method	90-100 lbs/ft ³
FINISHED RCM PRODUCT		
Organoclay Mass per Area	CETCO Test Method	0.8 lb/ft ²
Mat Grab Strength ²	ASTM D4632	90 lb. MARV
Hydraulic Conductivity ³	Mod. ASTM D4491	1 x 10 ⁻³ cm/sec minimum

NOTES:

¹ Apatite properties performed periodically on material prior to incorporation into the RCM.

² All tensile testing is performed in the machine direction.

³ Permittivity at constant head of 2 inches and converted to hydraulic conductivity using Darcy's Law and RCM thickness per ASTM D5199

North America: 847.851.1800 | 800.527.9948 | www.cetco.com

UPDATED: MAY 2017

© 2017 Minerals Technologies Inc. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.cetco.com. CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

