

FEATURES

- ▶ Narrow particle size distribution
- ▶ Fine particle size
- ▶ Process controlled top size

BENEFITS

- ▶ Economical solution as a pigment filler, reinforcement, or bodying agent
- ▶ Tailored for desired oil absorption and viscosity
- ▶ Controlled light scattering, opacity, rheology, and reinforcement
- ▶ Exceptional finished color in polymer systems

SHIPPING INFORMATION

MAGNUM FILL® SDL PCC ships from Ste. Genevieve, MO.

Product is available in 50 lb. bags and bulk.

For availability and minimum order quantity, contact customer service.

SALES OFFICES

Bethlehem, PA

800-801-1031

www.mineraltech.com

MAGNUM FILL® SDL

Precipitated Calcium Carbonate

Product Description

MAGNUM FILL® SDL is a light-density, high-brightness precipitated calcium carbonate designed as a functional filler for the coatings market. With its high oil absorption, MAGNUM FILL SDL is a versatile pigment for TiO₂ extension in coating applications.



Typical Physical Properties*

Form	Dry Powder
Crystal Type	Acicular Aragonite
Median Particle Size (Sedigraph, microns)	1.25 um
Surface Area (BET)	9.5 m ² /g
Dry Brightness (GE)	97.0
Oil Absorption (Rub Out) (ASTM D-281)	60.0
Residue (+325 mesh)	0.01%
Refractory Index	1.68
Specific Gravity	2.85
Einlehner Abrasion	5.0 mg
Hegman Grind	4+
Mohs Hardness	3
Apparent Dry Bulk Density - Loose	16 lbs/ft ³
Apparent Dry Bulk Density - Packed	32 lbs/ft ³
pH	9.5

Chemical Properties

Calcium Carbonate	CaCO ₃	98.6%
Iron As	Fe ₂ O ₃	0.05%
Moisture (Free H ₂ O)		0.5%

*Values listed are typical, not to be considered as specifications of the product.



The information provided may not be used for any purpose other than to identify prospective products consumers may be interested in purchasing. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use. All information given and recommendations made herein are based upon our research and are believed to be accurate, but no guarantee, either expressed or implied, is made with respect thereto or with respect to the infringement of any patent. SMI MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. Inconsistent terms and conditions contained in Buyer's purchase order shall not be binding on SMI unless reflected in writing signed by SMI's representative.